CYCOLOY™ CX2244ME resin

聚碳酸酯+丙烯腈丁二烯苯乙烯

SABIC Innovative Plastics

产品说明

CYCOLOY CX2244ME resin is a flame retardant PC/ABS blend featuring excellent balance of flow and impact together with UL-94 V0 rating at < 1mm. CYCOLOY CX2244ME resin also demonstrates improved chemical resistance to general hospital cleaners which can be considered for healthcare enclosure applications.

供应商联系方式

上海松翰塑化科技有限公司

电话: 13061808058

联系人: 赵先生

邮箱: sales@su-jiao.com

基本信息			
黄卡信息	E121562-546346		
添加剂	阻燃性		
特性	抗撞击性,良好	良好的流动性	耐化学性良好
	阻燃性		
用途	外壳	医疗器材	
加工方法	注射成型		
物理性能	额定值	单位制	测试方法
比重			
	1.19	g/cm³	ASTM D792
	1.20	g/cm³	ISO 1183
熔流率(熔体流动速率) (260°C/2.16 kg)	18	g/10 min	ASTM D1238
溶化体积流率(MVR) (260°C/2.16 kg)	15.0	cm³/10min	ISO 1133
收缩率 - 流动 (3.20 mm)	0.40 到 0.60	%	内部方法
吸水率			ISO 62
饱和, 23°C	0.20	%	ISO 62
平衡, 23°C, 50% RH	0.10	%	ISO 62
机械性能	额定值	单位制	测试方法
拉伸模量			
¹	2600	MPa	ASTM D638
	2600	MPa	ISO 527-2/1
抗张强度			
屈服 ²	65.0	MPa	ASTM D638
屈服	65.0	MPa	ISO 527-2/50
断裂 3	58.0	MPa	ASTM D638
断裂	50.0	MPa	ISO 527-2/50
伸长率			
屈服 4	4.1	%	ASTM D638
屈服	4.0	%	ISO 527-2/50
断裂 5	100	%	ASTM D638
断裂	90	%	ISO 527-2/50
弯曲模量			
50.0 mm 跨距 ⁶	2500	MPa	ASTM D790

7	2500	MPa	ISO 178
弯曲应力	2500	Wir d	150 170
 	96.0	MPa	ISO 178
屈服, 50.0 mm 跨距 ⁸	104	MPa	ASTM D790
冲击性能	 额定值	 单位制	
简支梁缺口冲击强度 ⁹	IXAL IH	十一元(h)	ISO 179/1eA
-30°C	10	kJ/m²	ISO 179/1eA
23°C	40	kJ/m²	ISO 179/1eA
を	40	K)/III-	150 179/1eA
-30°C	180	l/m	ASTM D256
23°C		J/m	
-30°C ¹⁰	700	J/m	ASTM D256
23°C ¹¹	10	kJ/m²	ISO 180/1A
	40	kJ/m²	ISO 180/1A
装有测量仪表的落镖冲击 (23°C, Total Energy)	65.0	J	ASTM D3763
热性能		单位制	
载荷下热变形温度			
1.8 MPa, 未退火, 3.20 mm	89.0	°C	ASTM D648
1.8 MPa, 未退火, 64.0 mm 跨距 ¹²	93.0	°C	ISO 75-2/Af
维卡软化温度			
			ASTM D1525, ISO
	110	°C	306/B50 11 ¹³
	113	°C	ISO 306/B120
Ball Pressure Test (75°C)	Pass		IEC 60695-10-2
线形热膨胀系数			ASTM E831, ISO 11359-2
流动:-40 到 40°C	7.5E-5	cm/cm/°C	ASTM E831, ISO 11359-2
横向:-40到 40°C	7.5E-5	cm/cm/°C	ASTM E831, ISO 11359-2
RTI Elec	90.0	°C	UL 746
RTI Imp	90.0	°C	UL 746
RTI	90.0	°C	UL 746
电气性能	额定值	单位制	测试方法
相比耐漏电起痕指数(CTI)	PLC 3		UL 746
高电弧燃烧指数(HAI)	PLC 0		UL 746
热丝引燃 (HWI)	PLC 3		UL 746
可燃性	额定值	单位制	测试方法
UL 阻燃等级			UL 94
0.750 mm	V-0		UL 94
1.50 mm	5VB		UL 94
灼热丝易燃指数 (3.00 mm)	960	°C	IEC 60695-2-12
热灯丝点火温度 (3.00 mm)	800	°C	IEC 60695-2-13
	额定值	单位制	
	80.0 到 90.0	°C	
干燥时间	2.0 到 4.0	hr	

建议的最大水分含量	0.020	%	
料斗温度	60.0 到 80.0	°C	
料筒后部温度	230 到 280	°C	
料筒中部温度	240 到 290	°C	
料筒前部温度	250 到 300	°C	
射嘴温度	250 到 300	°C	
加工(熔体)温度	250 到 300	°C	
模具温度	60.0 到 85.0	°C	
排气孔深度	0.030 到 0.075	mm	
备注			
1.	5.0 mm/min		
2.	类型 1, 50 mm/min		
3.	类型 1, 50 mm/min		
4.	类型 1, 50 mm/min		
5.	类型 1, 50 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*3 sp=62mm		
10.			
10.	80*10*3		
11.	80*10*3 80*10*3		