

Hostaform® C 27021 GV3/30

30% 玻璃珠
聚甲醛 (POM) 共聚物
Celanese Corporation

供应商联系方式

上海松翰塑化科技有限公司
电话: 13061808058
联系人: 赵先生
邮箱: sales@su-jiao.com

产品说明

Chemical abbreviation according to ISO 1043-1: POM
Molding compound ISO 9988- POM-K, M-GNR, 05-002, GB30
POM copolymer
With 30 % glass spheres reinforced, very easy flowing injection
molding type; low-warpage; high resistance to thermal and oxidative
degradation.
Burning rate ISO 3795 and FMVSS 302 < 100 mm/min for a thickness
more than 1 mm.
Ranges of applications: low-warpage and dimensionally stable molded
parts with higher rigidity and hardness.
FMVSS = Federal Motor Vehicle Safety Standard (USA)

基本信息

填料/增强材料	玻璃珠,30% 填料按重量		
特性	尺寸稳定性良好	低翘曲性	刚性,高
	流动性高	硬度高	
RoHS 合规性	联系制造商		
加工方法	注射成型		
多点数据	Shear Stress vs. Shear Rate (ISO 11403-1)		
树脂ID (ISO 1043)	POM		

物理性能	额定值	单位制	测试方法
密度	1.59	g/cm³	ISO 1183
溶化体积流率(MVR) (190°C/2.16 kg)	16.0	cm³/10min	ISO 1133
吸水率 (饱和, 23°C)	0.90	%	ISO 62

机械性能	额定值	单位制	测试方法
拉伸模量	3800	MPa	ISO 527-2/1A/1
拉伸应力 (屈服)	38.0	MPa	ISO 527-2/1A/50
拉伸应变 (屈服)	6.0	%	ISO 527-2/1A/50
标称拉伸断裂应变	12	%	ISO 527-2/1A/50
拉伸蠕变模量			ISO 899-1
1 hr	3300	MPa	ISO 899-1
1000 hr	2100	MPa	ISO 899-1
弯曲模量 (23°C)	3500	MPa	ISO 178

冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度			ISO 179/1eA
-30°C	3.0	kJ/m²	ISO 179/1eA
23°C	2.5	kJ/m²	ISO 179/1eA
简支梁无缺口冲击强度			ISO 179/1eU
-30°C	30	kJ/m²	ISO 179/1eU

23°C	30	kJ/m²	ISO 179/1eU
热性能	额定值	单位制	测试方法
热变形温度 (1.8 MPa, 未退火)	112	°C	ISO 75-2/A
熔融温度 ¹	166	°C	ISO 11357-3
线形热膨胀系数 - 流动	8.0E-5	cm/cm/°C	ISO 11359-2
电气性能	额定值	单位制	测试方法
表面电阻率	1.0E+14	ohms	IEC 60093
体积电阻率	1.0E+14	ohms-cm	IEC 60093
介电强度	40	kV/mm	IEC 60243-1
相对电容率			IEC 60250
100 Hz	5.00		IEC 60250
1 MHz	4.50		IEC 60250
耗散因数			IEC 60250
100 Hz	0.030		IEC 60250
1 MHz	8.0E-3		IEC 60250
漏电起痕指数	600	V	IEC 60112
注射	额定值	单位制	
干燥温度	100 到 120	°C	
干燥时间	3.0 到 4.0	hr	
建议的最大水分含量	0.15	%	
料斗温度	20.0 到 30.0	°C	
料筒后部温度	170 到 180	°C	
料筒中部温度	180 到 190	°C	
料筒前部温度	190 到 200	°C	
射嘴温度	190 到 210	°C	
加工(熔体)温度	190 到 210	°C	
模具温度	80.0 到 120	°C	
注塑压力	60.0 到 120	MPa	
注射速度	慢		
保压	60.0 到 120	MPa	
背压	0.00 到 2.00	MPa	
注射说明			
Manifold Temperature: 190 to 210°CZone 4 Temperature: 190 to 210°CFeed Temperature: 60 to 80°C			
备注			
1.	10°C/min		