

# Hostaform® C 27021 AS

聚甲醛 ( POM ) 共聚物  
Celanese Corporation

## 产品说明

POM copolymer  
Antistatistical modified; very easy flowing Injection molding type; the antistatistical effect improves, when the molded part absorbs enough humidity; good chemical resistance to solvents, fuel and strong alkalis as well as good hydrolysis resistance; high resistance to thermal and oxidative degradation.  
Hostaform C 27021 AS is suggested for dissipation of minor buildup of static electricity that might occur with standard type grades. However, it is not intended for use in fuel system components where static dissipation is critical to part performance. Please refer to Celanese's ESD (electrostatic dissipative) grades for those applications  
Preliminary Datasheet

### 供应商联系方式

上海松翰塑化科技有限公司  
电话: 13061808058  
联系人: 赵先生  
邮箱: sales@su-jiao.com

### 基本信息

|                             |         |                        |                 |
|-----------------------------|---------|------------------------|-----------------|
| 添加剂                         | 抗静电性    |                        |                 |
| 特性                          | 抗静电性    | 抗溶剂性                   | 良好的流动性          |
|                             | 耐化学性良好  | 耐碱                     | 耐燃油性            |
|                             | 耐热性,高   | 耐水解性                   |                 |
| RoHS 合规性                    | 联系制造商   |                        |                 |
| 物理性能                        | 额定值     | 单位制                    | 测试方法            |
| 密度                          | 1.41    | g/cm <sup>3</sup>      | ISO 1183        |
| 溶化体积流率(MVR) (190°C/2.16 kg) | 25.0    | cm <sup>3</sup> /10min | ISO 1133        |
| 收缩率                         |         |                        | ISO 294-4       |
| 垂直流动方向                      | 1.8     | %                      | ISO 294-4       |
| 流动方向                        | 1.9     | %                      | ISO 294-4       |
| 机械性能                        | 额定值     | 单位制                    | 测试方法            |
| 拉伸模量                        | 2650    | MPa                    | ISO 527-2/1A/1  |
| 拉伸应力 (屈服)                   | 62.0    | MPa                    | ISO 527-2/1A/50 |
| 拉伸应变 (屈服)                   | 8.0     | %                      | ISO 527-2/1A/50 |
| 标称拉伸断裂应变                    | 20      | %                      | ISO 527-2/1A/50 |
| 冲击性能                        | 额定值     | 单位制                    | 测试方法            |
| 简支梁缺口冲击强度                   |         |                        | ISO 179/1eA     |
| -30°C                       | 4.5     | kJ/m <sup>2</sup>      | ISO 179/1eA     |
| 23°C                        | 5.0     | kJ/m <sup>2</sup>      | ISO 179/1eA     |
| 简支梁无缺口冲击强度                  |         |                        | ISO 179/1eU     |
| -30°C                       | 120     | kJ/m <sup>2</sup>      | ISO 179/1eU     |
| 23°C                        | 120     | kJ/m <sup>2</sup>      | ISO 179/1eU     |
| 热性能                         | 额定值     | 单位制                    | 测试方法            |
| 熔融温度 <sup>1</sup>           | 166     | °C                     | ISO 11357-3     |
| 线形热膨胀系数 - 流动                | 1.1E-4  | cm/cm/°C               | ISO 11359-2     |
| 电气性能                        | 额定值     | 单位制                    | 测试方法            |
| 表面电阻率                       | 1.0E+12 | ohms                   | IEC 60093       |

| 注射       | 额定值                  | 单位制 |
|----------|----------------------|-----|
| 加工(熔体)温度 | 190 到 230            | °C  |
| 模具温度     | 80.0 到 120           | °C  |
| 螺杆长径比    | 15.0:1.0 to 25.0:1.0 |     |
| 备注       |                      |     |
| 1.       | 10°C/min             |     |