

LEXAN™ EXL1112 resin

聚碳酸酯

SABIC Innovative Plastics

产品说明

LEXAN EXL1112 polycarbonate (PC) siloxane copolymer resin is a high flow opaque injection molding (IM) grade. This resin offers good low temperature (-20 C) ductility in combination with excellent processability and release with opportunities for shorter IM cycle times compared to standard PC. LEXAN EXL1112 resin is a product available in wide range of opaque colors and may be an excellent candidate for a wide variety of applications.

供应商联系方式

上海松翰塑化科技有限公司
电话: 13061808058
联系人: 赵先生
邮箱: sales@su-jiao.com

基本信息

特性	共聚物	可加工性,良好	快的成型周期
	流动性高	脱模性能良好	延展性

用途	通用	
外观	不透明	可用颜色
加工方法	注射成型	

物理性能	额定值	单位制	测试方法
比重			
--	1.18	g/cm ³	ASTM D792
--	1.19	g/cm ³	ISO 1183
熔速率(熔体流动速率) (300°C/1.2 kg)	17	g/10 min	ASTM D1238
溶化体积速率(MVR) (300°C/1.2 kg)	16.0	cm ³ /10min	ISO 1133
收缩率			内部方法
流动 : 3.20 mm	0.40 到 0.80	%	内部方法
横向流动 : 3.20 mm	0.40 到 0.80	%	内部方法
吸水率			ISO 62
饱和, 23°C	0.35	%	ISO 62
平衡, 23°C, 50% RH	0.15	%	ISO 62

硬度	额定值	单位制	测试方法
球压硬度 (H 358/30)	95.0	MPa	ISO 2039-1

机械性能	额定值	单位制	测试方法
拉伸模量			
-- ¹	2280	MPa	ASTM D638
--	2150	MPa	ISO 527-2/1
抗张强度			
屈服 ²	58.1	MPa	ASTM D638
屈服	57.0	MPa	ISO 527-2/50
断裂 ³	58.7	MPa	ASTM D638
断裂	55.0	MPa	ISO 527-2/50
伸长率			
屈服 ⁴	5.8	%	ASTM D638

屈服	5.0	%	ISO 527-2/50
断裂 ⁵	110	%	ASTM D638
断裂	100	%	ISO 527-2/50
弯曲模量			
50.0 mm 跨距 ⁶	2320	MPa	ASTM D790
-- ⁷	2240	MPa	ISO 178
弯曲应力			
--	85.0	MPa	ISO 178
屈服, 50.0 mm 跨距 ⁸	95.1	MPa	ASTM D790
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度 ⁹			ISO 179/1eA
-30°C	25	kJ/m²	ISO 179/1eA
23°C	60	kJ/m²	ISO 179/1eA
简支梁无缺口冲击强度 ¹⁰			ISO 179/1eU
-30°C	无断裂		ISO 179/1eU
23°C	无断裂		ISO 179/1eU
悬壁梁缺口冲击强度			
-30°C	670	J/m	ASTM D256
23°C	750	J/m	ASTM D256
-30°C ¹¹	20	kJ/m²	ISO 180/1A
23°C ¹²	55	kJ/m²	ISO 180/1A
无缺口伊佐德冲击强度 ¹³			ISO 180/1U
-30°C	无断裂		ISO 180/1U
23°C	无断裂		ISO 180/1U
装有测量仪表的落镖冲击 (23°C, Total Energy)	69.6	J	ASTM D3763
热性能	额定值	单位制	测试方法
载荷下热变形温度			
0.45 MPa, 未退火, 3.20 mm	137	°C	ASTM D648
0.45 MPa, 退火 ¹⁴	136	°C	ISO 75-2/Be
1.8 MPa, 未退火, 3.20 mm	124	°C	ASTM D648
1.8 MPa, 未退火, 100 mm 跨距 ¹⁵	125	°C	ISO 75-2/Ae
维卡软化温度			
--	144	°C	ASTM D1525, ISO 306/B50 12 ¹⁶
--	145	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
线形热膨胀系数			
流动：-40 到 40°C	7.2E-5	cm/cm/°C	ASTM E831
流动：23 到 80°C	7.5E-5	cm/cm/°C	ISO 11359-2
横向：-40 到 40°C	7.6E-5	cm/cm/°C	ASTM E831
横向：23 到 80°C	7.5E-5	cm/cm/°C	ISO 11359-2
RTI Elec	130	°C	UL 746

RTI Imp	120	°C	UL 746
RTI	125	°C	UL 746
可燃性	额定值	单位制	测试方法
灼热丝易燃指数			IEC 60695-2-12
0.800 mm	850	°C	IEC 60695-2-12
3.00 mm	960	°C	IEC 60695-2-12
热灯丝点火温度			IEC 60695-2-13
1.00 mm	875	°C	IEC 60695-2-13
3.00 mm	875	°C	IEC 60695-2-13
极限氧指数	32	%	ISO 4589-2
注射	额定值	单位制	
干燥温度	121	°C	
干燥时间	3.0 到 4.0	hr	
干燥时间,最大	48	hr	
建议的最大水分含量	0.020	%	
建议注射量	40 到 60	%	
料筒后部温度	217 到 293	°C	
料筒中部温度	282 到 304	°C	
料筒前部温度	293 到 316	°C	
射嘴温度	288 到 310	°C	
加工(熔体)温度	293 到 316	°C	
模具温度	71.0 到 93.0	°C	
背压	0.345 到 0.689	MPa	
螺杆转速	40 到 70	rpm	
排气孔深度	0.025 到 0.076	mm	
备注			
1.	50 mm/min		
2.	类型 1, 50 mm/min		
3.	类型 1, 50 mm/min		
4.	类型 1, 50 mm/min		
5.	类型 1, 50 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*3 sp=62mm		
10.	80*10*3 sp=62mm		
11.	80*10*3		
12.	80*10*3		
13.	80*10*3		
14.	4 hr, 80°C		
15.	120*10*4 mm		
16.	标准 B (120°C/h), 载荷2 (50N)		