

LEXAN™ CFR7431 resin

聚碳酸酯

SABIC Innovative Plastics

产品说明

LEXAN CFR7431 Polycarbonate (PC) resin is a non-filled, injection moldable grade. This non-chlorinated, non-brominated flame retardant PC has an UL-94 V0 rating at 1.2 mm / 5VA rating at 3.0mm and is UV stabilized(F1 rating) providing additional weathering capability. LEXAN CFR7431 is available in clear transparent and tinted color options that is an excellent candidate for a wide variety of applications.

供应商联系方式

上海松翰塑化科技有限公司

电话: 13061808058

联系人: 赵先生

邮箱: sales@su-jiao.com

基本信息

黄卡信息	E121562-100922880		
添加剂	紫外线稳定剂		
特性	Chlorine Free	耐气候影响性能良好	无溴
	阻燃性		
外观	可用颜色	清晰/透明	
加工方法	注射成型		

物理性能	额定值	单位制	测试方法
比重			
--	1.19	g/cm³	ASTM D792
--	1.20	g/cm³	ISO 1183
熔速率(熔体流动速率) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
溶化体积速率(MVR) (300°C/1.2 kg)	9.00	cm³/10min	ISO 1133
收缩率			内部方法
流动：3.20 mm	0.55 到 0.75	%	内部方法
横向流动：3.20 mm	0.60 到 0.80	%	内部方法
吸水率			ISO 62
饱和, 23°C	0.13	%	ISO 62
平衡, 23°C, 50% RH	0.10	%	ISO 62
室外适用性	f1		UL 746C

机械性能	额定值	单位制	测试方法
拉伸模量			
-- ¹	2520	MPa	ASTM D638
--	2350	MPa	ISO 527-2/1
抗张强度			
屈服 ²	67.0	MPa	ASTM D638
屈服	66.0	MPa	ISO 527-2/50
断裂 ³	55.0	MPa	ASTM D638
断裂	53.0	MPa	ISO 527-2/50
伸长率			
屈服 ⁴	6.0	%	ASTM D638
屈服	6.0	%	ISO 527-2/50

断裂 ⁵	55	%	ASTM D638
断裂	56	%	ISO 527-2/50
弯曲模量			
50.0 mm 跨距 ⁶	2450	MPa	ASTM D790
-- ⁷	2450	MPa	ISO 178
弯曲应力			
--	101	MPa	ISO 178
屈服, 50.0 mm 跨距 ⁸	107	MPa	ASTM D790
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度 ⁹			ISO 179/1eA
-30°C	7.0	kJ/m²	ISO 179/1eA
23°C	10	kJ/m²	ISO 179/1eA
简支梁无缺口冲击强度 ¹⁰			ISO 179/1eU
-30°C	无断裂		ISO 179/1eU
23°C	无断裂		ISO 179/1eU
悬壁梁缺口冲击强度			
-30°C	81	J/m	ASTM D256
23°C	100	J/m	ASTM D256
-30°C ¹¹	8.0	kJ/m²	ISO 180/1A
23°C ¹²	9.0	kJ/m²	ISO 180/1A
无缺口悬臂梁冲击			ASTM D4812, ISO 180/1U
-30°C	无断裂		ASTM D4812, ISO 180/1U
23°C	无断裂		ASTM D4812, ISO 180/1U
装有测量仪表的落镖冲击 (23°C, Total Energy)	64.0	J	ASTM D3763
热性能	额定值	单位制	测试方法
载荷下热变形温度			
0.45 MPa, 未退火, 3.20 mm	131	°C	ASTM D648
0.45 MPa, 未退火, 100 mm 跨距 ¹³	131	°C	ISO 75-2/Be
1.8 MPa, 未退火, 3.20 mm	120	°C	ASTM D648
1.8 MPa, 未退火, 100 mm 跨距 ¹⁴	120	°C	ISO 75-2/Ae
维卡软化温度			
--	136	°C	ASTM D1525 ¹⁵
--	137	°C	ISO 306/B50
--	139	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
线形热膨胀系数			
流动：-40 到 40°C	6.7E-5	cm/cm/°C	ASTM E831
流动：23 到 80°C	7.7E-5	cm/cm/°C	ISO 11359-2
横向：-40 到 40°C	6.7E-5	cm/cm/°C	ASTM E831

横向 : 23 到 80°C	7.9E-5	cm/cm/°C	ISO 11359-2
RTI Elec	125	°C	UL 746
RTI Imp	120	°C	UL 746
RTI	125	°C	UL 746
电气性能	额定值	单位制	测试方法
介电常数 (1.10 GHz)	2.79		ASTM ES7-83
耗散因数 (1.10 GHz)	5.7E-3		ASTM ES7-83
可燃性	额定值	单位制	测试方法
UL 阻燃等级			UL 94
0.400 mm	V-2		UL 94
1.00 mm	V-1		UL 94
1.20 mm	V-0		UL 94
3.00 mm	5VA		UL 94
灼热丝易燃指数 (1.20 mm)	960	°C	IEC 60695-2-12
热灯丝点火温度 (1.20 mm)	850	°C	IEC 60695-2-13
光学性能	额定值	单位制	测试方法
透射率			内部方法
1000 µm	> 90.0	%	内部方法
2000 µm	> 89.0	%	内部方法
3000 µm	> 88.0	%	内部方法
注射	额定值	单位制	
干燥温度	121	°C	
干燥时间	3.0 到 4.0	hr	
干燥时间,最大	48	hr	
建议的最大水分含量	0.020	%	
建议注射量	40 到 60	%	
料筒后部温度	260 到 282	°C	
料筒中部温度	271 到 293	°C	
料筒前部温度	282 到 304	°C	
射嘴温度	277 到 299	°C	
加工(熔体)温度	282 到 304	°C	
模具温度	71.1 到 93.3	°C	
背压	0.345 到 0.689	MPa	
螺杆转速	40 到 70	rpm	
排气孔深度	0.025 到 0.076	mm	
备注			
1.	50 mm/min		
2.	类型 1, 50 mm/min		
3.	类型 1, 50 mm/min		
4.	类型 1, 50 mm/min		
5.	类型 1, 50 mm/min		
6.	1.3 mm/min		

7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*3 sp=62mm
10.	80*10*3 sp=62mm
11.	80*10*3
12.	80*10*3
13.	120*10*4 mm
14.	120*10*4 mm
15.	标准 B (120°C/h), 载荷2 (50N)